

REPCON HS

HIGH STRENGTH CONCRETE REPAIR MORTAR

REPCON HS is a single component, high strength concrete repair material. This cement based mortar is designed for repairing structural concrete members by hand troweling or low pressure spraying.

PRIMARY APPLICATIONS:

- Exterior or interior applications
- Parking and bridge structures
- Parapet walls
- Pre-cast or cast-in place vertical concrete repairs
- Docks, piers and wharfs

FEATURES/BENEFITS:

- One component material ready to use with only addition of clean water
- Helps protect rebar from corrosion
- Applied up to 30 mm per lift
- Very low chloride permeability
- Sulphate resistant
- Very low shrinkage
- High abrasion resistance
- Long working time for easy placement

PACKAGING/YIELD:

REPCON HS is packaged in 25 kg bags. Yield is 0.0138 m³/ bag when mixed with approximately 4 liters of water.

COVERAGE:

One bag of **REPCON HS** will cover approximately 1.06 m² when placed at an average depth of 13 mm. **REPCON HS** may be placed in thickness from 6 mm to 30 mm in depth per lift.

NOTE: This product requires a curing compound which must be ordered separately. Consult the curing information.

TECHNICAL INFORMATION:

Typical Engineering Data 23°C

The following results were developed under laboratory conditions

Fresh wet density : 2100 kg/m³

Working time : 1:00 Hour

Compressive strength

ASTM C-109 50mm cubes

Age

1 day

3 days

7 days

28 days

Strength

25 N/mm²

35 N/mm²

45 N/mm²

64 N/mm²

Flexural strength

28 days

1150 psi (8 MPa)

Slant Shear bond Strength ASTM C-882 (modified)

28 days

3600 psi (25 MPa)

Water absorption:

ASTM C 642

>2%

Chloride permeability

AASHTO T227

28 day's

385 coulombs

Co-Efficient of the thermal expansion:

10 to 11x10⁻⁶/mm/mm/°C

Chemical Resistance:

REPCON HS is highly resistant against: Acid gases, water, Chloride ions.

DIRECTIONS FOR USE:

Surface preparation - The concrete must be clean and rough. All oil, dirt, debris, paint and unsound concrete must be removed. The surface must be mechanically using a bush hammer, sand blaster or jack hammer which will give a surface profile of a minimum 3.2 mm and expose the coarse aggregate of the concrete. The final step in cleaning should be the complete removal of all residues with a vacuum cleaner or pressure washing.

Exposed Reinforcing Steel - Exposed rebar may be treated with an anti-corrosive coating such as EPOCHEM or ZINC RICH PRIMER. Remove all loose rust and scaling, preferably by sand blasting to white metal prior to coating the rebar.

Bonding-The substrate shall be wetted to prevent any moisture evaporation from the bonding agent or from the repair materials. After the surface has been prepared, all areas must be primed with EPOCHEM or EPOPRIME LP or with a slurry coat of CEMPOL SBR. A slurry coat of this product is by mixing the material as indicated in the CEMPOL SBR literature.

“High Quality Construction Chemicals”

CONSTRUCTION MATERIAL CHEMICAL INDUSTRIES

P.O. Box 7137, Dammam 31462, Saudi Arabia, Tel: 00966-13-8471450; Fax: 00966-13-8471575

Email: tech@cmci-sa.com, Web: www.cmci-sa.com

Mixing: REPCON HS can be mixed by using a drill and “jiffy” type mixer. Use paddle type mortar mixer for large placements.

Add the appropriate amount of water for the batch size and then add the dry product. Mix a minimum of 5 minutes. The mixed product should be quickly transported to the repair area and placed immediately.

Placement - Product should be placed up to 30 mm per lift. Trowel into the place before the next lift. If additional lifts will be placed after the product has hardened, crosshatch the surface of the previous lift to provide for a secure bond for the next lift.

Finishing - Finish the repair material to the desired texture to match the surrounding concrete. Do not add additional water to the surface during finishing operation.

Curing and Sealing - Proper curing procedures are important to ensure the durability of the repair. To prevent surface cracking, cure the repair mortar with a high solids curing compound such as KUREKOTE 75 VOX.

(NOTE: DO NOT USE A SOLVENT BASED CURING COMPOUND ON THIS PRODUCT)
Allow the curing compound to dry. In hot, windy or direct sunlight situations, apply a second coat of curing compound after the initial coat is dry. If a curing compound is not desired, wet cure for minimum of three days.

Clean-up- Clean all tools and equipments with water before the material hardens.

PRECAUTIONS/LIMITATIONS:

- In adverse temperatures, follow ACI recommendations of hot/cold weather concreting practices.
- Use only potable water for mixing
- Store product in a dry place

TD/PDS/0610/B

QUALITY STATEMENT

CMCI manufacture its products at their manufacturing facility in Saudi Arabia as per the Quality Procedures certified to conform with Quality Management System described in ISO9000 series

CMCI provides a comprehensive technical support system for its full range of high performance construction products. CMCI also offers full technical field support to consultants, Architects, Contractors, applicators and End Users

The Technical Specification information and recommendation given are based on the current technical knowledge and the user or his representative is recommended to check the suitability of the product. CMCI reserves the right to amend the technical characteristic of the product as part of ongoing research and development. As the work execution is beyond the direct and continuous control of CMCI no guaranty and or responsibility is assumed on the performance of work completion executed with use of our products.